

TEST REPORT

LAB NO. : (8820)064-0054 DATE : Mar 24, 2020

PAGE : 1 OF 8

APPLICANT : FLASHBAY ELECTRONICS

XIFENGCHENG INDUSTRIAL PARK, FUHAI STREET,

BAOAN DISTRICT SHENZHEN CITY

DATE OF SUBMISSION: MAR 4, 2020

TEST PERIOD : MAR 4, 2020 TO MAR 24, 2020

SAMPLE DESCRIPTION: PHONE GRIPS

Style No.: HOOP

GRIP

Sample Size: 5



BUREAU VERITAS SHENZHEN CO.,LTD DONGGUAN BRANCH

Harvey Xue

Manager, Analytical Lab

RT/Tina Ye/Sammy Du

REMARK

If there are questions or concerns on this report, please contact the following persons:

Report Enquiry: (86) 0769 89952999 Ext. 8175 CPSAnalytical.DG@bureauveritas.com

Business Contact: (86) 0769 85893595

This report shall not be reproduced except in full, without the written approval of our laboratory.



LAB NO. : (8820)064-0054 DATE : Mar 24, 2020 PAGE : 2 OF 8


SUMMARY OF TEST RESULTS

TEST REQUESTED	CONCLUSION	REMARK
European Parliament and Council Directive 2011/65/EU on the		
Restriction of the Use of Certain Hazardous Substances in	PASS	
Electrical and Electronic Equipment (RoHS) with its	-	
Amendment Directive 2015/863/EU		
The BBP/DBP/DEHP/DIBP content requirements of the European		
Parliament and Council Directive 2011/65/EU on the Restriction of		
the Use of Certain Hazardous Substances in Electrical and	PASS	-
Electronic Equipment (RoHS) with its Amendment Directive		
2015/863/EU		



LAB NO. : (8820)064-0054 DATE : Mar 24, 2020 PAGE : 3 OF 8

Photo of the Submitted Sample





LAB NO. : (8820)064-0054 DATE : Mar 24, 2020 PAGE : 4 OF 8

Test Item Description and Photo List

Test Item(s)	Sample Photo	Item / Component Description(s)	Location(s)	Style(s)
I001		White foam	Adhesive foam, big phone grip	-
I002		White plastic	Base, big phone grip	-
I003		White plastic	Big buckle, big phone grip	-
I004		White plastic	Plate, holder, big phone grip	-
I005		White plastic	Holder, big phone grip	-
I006		White plastic	Small buckle, big phone grip	-
I007		Black foam with glue	Adhesive foam, small phone grip	-
I008		Transparent plastic with paper	Plate, small phone grip	-
I009		Silvery metal	Base, small phone grip	-
I010		Silvery metal	Ring, small phone grip	-
I011		Silvery metal	Plate, small phone grip	-
I012		Transparent plastic	Washer, small phone grip	-
I013		Silvery metal	Washer, small phone grip	-
I014		Black plated silvery metal	Shaft, small phone grip	-



LAB NO. : (8820)064-0054 DATE : Mar 24, 2020 PAGE : 5 OF 8

TEST RESULT

Compliance Test – European Parliament and Council Directive 2011/65/EU on the Restriction of the Use of Certain Hazardous Substances in Electrical and Electronic Equipment (RoHS) with its Amendment Directive 2015/863/EU

Test Method: See Appendix.

See Analytes and their corresponding Maximum Allowable Limit in Appendix

-	Result						
Parameter	Lead (Pb)	Cadmium	Mercury	Chromium	PBBs	PBDEs	Conclusion
	Lead (10)	(Cd)	(Hg)	VI (Cr VI)		I DDL3	
Unit			mg	g/kg			-
Test Item(s)	-	-	-	-	-	-	-
I001	ND	ND	ND	ND	ND	ND	PASS
I002	ND	ND	ND	ND	ND	ND	PASS
I003	ND	ND	ND	ND	ND	ND	PASS
I004	ND	ND	ND	ND	ND	ND	PASS
I005	ND	ND	ND	ND	ND	ND	PASS
I006	ND	ND	ND	ND	ND	ND	PASS
I007	ND	ND	ND	ND	ND	ND	PASS
I008	ND	ND	ND	ND	ND	ND	PASS
I009	ND	ND	ND	ND	NA	NA	PASS
I010	ND	ND	ND	Negative*	NA	NA	PASS
I011	ND	ND	ND	ND	NA	NA	PASS
I012	ND	ND	ND	ND	ND	ND	PASS
I013	ND	ND	ND	Negative*	NA	NA	PASS
I014	ND	ND	ND	ND	NA	NA	PASS

Note / Key:

 $ND = Not \ detected$ ">" = Greater than "<" = Less than $NR = Not \ requested$ $mg/kg = milligram(s) \ per \ kilogram = ppm = part(s) \ per \ million$ $<math>NA = Not \ applicable$ % = percent $10000 \ mg/kg = 1 \ \%$

Detection Limit: See Appendix.

Remark:

- The testing approach is listed in table of Appendix.
- * denotes as reported result(s) was (were) performed by wet chemistry method. Others were screened by XRF. For XRF screening, the result(s) of Cr VI was (were) reported as total chromium and the result(s) of PBBs and PBDEs was (were) reported as total bromine. Also, the XRF result(s) may be different to the actual content based on various factors including, but not limit to, sample size, thickness, area, non-uniformity composition, surface flatness.
- According to European Council Directive 2011/65/EU, Article 5 "Adaptation of the Annexes to scientific and technical progress", exemption(s) should be granted to the materials and components of Test Item(s) in the lists in Annexes III and IV of this directive.
- The items 009 was resubmitted by client dated on Mar 19, 2020.



LAB NO. : (8820)064-0054 DATE : Mar 24, 2020 PAGE : 6 OF 8

APPENDIX

List of Analytes and their Corresponding Test Methods, Detection Limit and Maximum Allowable Limit

[Compliance Test for European Parliament and Council Directive 2011/65/EU]:

	Name of Analytes	Detection Limit (mg/kg)				Movim
No.		X-ray fluorescence (XRF) ^[a]				Maximum Allowable
		Plastic	Metallic / glass / ceramic	Others	Wet Chemistry	Limit (mg/kg)
1	Lead (Pb)	100	200	200	10 ^[b]	1000
2	Cadmium (Cd)	50	50	50	10 ^[b]	100
3	Mercury (Hg)	100	200	200	10 ^[c]	1000
4	Chromium (Cr)	100	200	200	NA	NA
5	Chromium VI (Cr VI)	NA	NA	NA	3 ^[g, h] / 10 ^[d] / See ^[e, j]	1000 / Negative ^[j]
6	Bromine (Br)	200	NA	200	NA	NA
7	Polybromobiphenyls (PBBs) - Bromobiphenyl (MonoBB) - Dibromobiphenyl (DiBB) - Tribromobiphenyl (TriBB) - Tetrabromobiphenyl (TetraBB) - Pentabromobiphenyl (PentaBB) - Hexabromobiphenyl (HexaBB) - Heptabromobiphenyl (HeptaBB) - Octabromobiphenyl (OctaBB) - Nonabromobiphenyl (NonaBB) - Decabromobiphenyl (DecaBB)	NA	NA	NA	Each 50 ^[f]	Sum 1000
8	Polybromodiphenyl ethers (PBDEs) - Bromodiphenyl ether (MonoBDE) - Dibromodiphenyl ether (DiBDE) - Tribromodiphenyl ether (TriBDE) - Tetrabromodiphenyl ether (TetraBDE) - Pentabromodiphenyl ether (PentaBDE) - Hexabromodiphenyl ether (HexaBDE) - Heptabromodiphenyl ether (HeptaBDE) - Octabromodiphenyl ether (OctaBDE) - Nonabromodiphenyl ether (NonaBDE) - Decabromodiphenyl ether (DecaBDE)	NA	NA	NA	Each 50 ^[f]	Sum 1000



LAB NO. : (8820)064-0054 DATE : Mar 24, 2020 PAGE : 7 OF 8

List of Analytes and their Corresponding Test Methods, Detection Limit and Maximum Allowable Limit [Compliance Test for European Parliament and Council Directive 2011/65/EU]:

- NA = Not applicable
- [a] Test method with reference to International Standard IEC 62321-3-1: 2013.
- Test method with reference to International Standard IEC 62321-5: 2013.
- [c] Test method with reference to International Standard IEC 62321-4: 2017.
- [d] Polymers and Electronics Test method with reference to International Standard IEC 62321-7-2:2017.
- [e] Metal Test method with reference to International Standard IEC 62321-7-1: 2015.
- Test method with reference to International Standard IEC 62321-6: 2015.
- [g] Leather Test method International Standard ISO 17075-1:2017.
- Other Than Metal, Leather, Polymers and Electronics Test method with reference to International Standard ISO 17075-1:2017.
- The principle of this method was evaluated and supported by two studies organized by IEC TC 111 WG3. These studies were focused on detecting the presence of Cr VI in the corrosion protection coatings on metallic samples.
- Result(s) of Cr VI for metallic material(s) was (were) expressed in term of positive and negative. Negative means the absence of Cr VI on the tested areas and the result(s) was (were) regarded as in compliance with European Parliament and Council Directive 2011/65/EU, Article 4(1). While, positive means the presence of Cr VI on tested areas and the result(s) was (were) regarded as in conflict with European Parliament and Council Directive 2011/65/EU, Article 4(1).

Testing Approach [Compliance Test for European Parliament and Council Directive 2011/65/EU]:

The testing approach was with reference to the following document(s).

- 1 International Standards IEC 62321-1: 2013 and IEC 62321-2: 2013
- 2 "RoHS Enforcement Guidance Document Version 1" by EU RoHS Enforcement Authorities Informal Network. (May 2006)
- 3 "RoHS Regulations Government Guidance Notes" by United Kingdom Department for Business Innovation & Skills. (February 2011)
- 4 "Final Report to RoHS substances (Hg, Pb, Cr(VI), Cd, PBB and PBDE) in electrical and electronic equipment in Belgium" by Belgium Federal Public Service Health, Food Chain Safety and Environment. (November 2005)



LAB NO. : (8820)064-0054 DATE : Mar 24, 2020 PAGE : 8 OF 8

TEST RESULT

BBP/DBP/DEHP/DIBP Content – European Parliament and Council Directive 2011/65/EU on the Restriction of the Use of Certain Hazardous Substances in Electrical and Electronic Equipment (RoHS) with its Amendment Directive 2015/863/EU

Test Method : With reference to International Standard IEC 62321-8:2017

Test Parameter:	BBP	DBP	DEHP	DiBP	-	
Limit (%):	0.1	0.1	0.1	0.1	-	
Test Item(s)		Result (%)				
I001+I002+I003 +I004+I005	ND	ND	ND	ND	PASS	
I006+I007+I012	ND	ND	ND	ND	PASS	
I008	ND	ND	ND	ND	PASS	

Note / key:

BBP = Butyl benzyl phthalate (CAS No: 85-68-7)

DBP = Dibutyl phthalate (CAS No: 84-74-2)

DEHP = Di(2-ethylhexyl) phthalate (CAS No: 117-81-7)

DiBP = Diisobutyl phthalate (CAS No: 84-69-5)

ND = Not detected % = percent 10000 mg/kg = 1 %

mg/kg = milligram(s) per kilogram Detection Limit (%) : Each 0.005

Remark:

- The amendment will be effective on 22 July 2019. For medical devices and control instruments, effective date will be 22 July 2021.
- The composite test sample(s) of the submitted samples was prepared in the manner requested by the client, when subject to the test performed.

*** End of Report ***